



## Trial Material Evaluation

Material Data					
Material Name	Material Kind	quantity ton	Supplier	Place of use	Notes
Graphite electrode 700 mm	Graphite	70.546	JIANG LONG	EAF-SMP2	
Work Data					
Quantity used			Date of use	Notes during use	
70.546			28/01/2021		
Notes after work					
<p>No breakage operation                      No lost due to bad joints or missconnection.                      No sever craks</p> <p>Average consumption rate was nearly <b><u>1.50 kg/ton</u></b></p>					
Conclusion					
The consumption rate is <b><u>1.50 kg/ton</u></b>					
MS Sec. Head Wael Atta Elsayed  2/2/2021		Production Manger Hossam Farghaly  8.02.2021		Plant Manger Khaled Saied 